


MECOBOND® - STANDARDS TYPE C

MECOBOND® Dr. Betz GmbH, Saarner Straße 433, 45478 Mülheim a. d. Ruhr/ Germany
Tel.: +49(0)208 589433 Fax: +49(0)208 589434 email: info@mecobond.de

MECOBOND® standards are standardised cylinder steel bodies with an integrated heat-conducting element (copper-inlet) from which mold cores can be manufactured economically in the characteristic MECOBOND® design.

Soft annealed state:
Steel (1.2343/ x38CrMoV51) < 32 HRC)

Heat conductivities:
Steel (1.2343/x38CrMoV51) 25 W/m.K
MECOBOND®-copper at least 350 W/m.K



Type	diameter copper-inlet D	length copper-inlet L	price ex works	order number of pieces
MC3	3,0 mm	30 mm	<div> <p>Euro 325.- /piece (soft*)</p> <p>Euro 350.- /piece (hardened)</p> <p>*extra MECOBOND hardening</p> <p>Euro 150,-/piece</p> <p>01.01.2012</p> </div>	MC3
MC3,5	3,5 mm	35 mm		MC3,5.....
MC4	4,0 mm	40 mm		MC4
MC6	6,0 mm	60 mm		MC6
MC8	8,0 mm	80 mm		MC8
MC10	10,0 mm	100 mm		MC10
MC12	12,0 mm	120 mm		MC12
MC14	14,0 mm	140 mm		MC14
MC16	16,0 mm	160 mm		MC16

FAX +49(0)208 589434 or
email info@mecobond.de

company:

department

name phone

.....
(date, signature)